

X-Seal EP Primer

High performance epoxy primer for use with sealants in immersed conditions

Product Description

X-Seal EP primer is a two component epoxy primer suitable for use with all X-Seal silicone, polyurethane, polysulphide and hybrid polymer sealants. It is suitable for use in immersed conditions and can also be applied to high humidity substrates.

The product can be part mixed as the mixing ratio is 1 to 1 by volume.

Advantages

- Low viscosity
- Penetrating
- Enhances bond
- Stops out gassing

Application Properties

	10C	20C	30C	40C
Tack free time	12h	6h	3h	90mins
Min. sealant application time	2h	1h	30mins	15mins
Max. sealant application time	16h	8h	4h	2h
Mixing ratio	1:1 by volume			

Volatile Organic Content

VOC = 430 g/L

Theoretical Coverage

X-Seal EP Primer - 6 - 8 m² per kg
1 Kg of X-Seal EP Primer is sufficient for 150lm joint x 10mm depth.

Actual coverage will depend on wastage and surface profile and can be up to 50% higher than the theoretical coverage.

Packaging

1 and 5 Kg Packs

Shelf Life

12 months when stored below 30C under shade in a dry environment.

Application Guidelines

Joint sealant systems should be applied by experienced coating crews. X-Calibur provides detailed method statements on all its products for use in various applications. These must be referred to prior to starting work. The information below is a summary intended for guidance only.

Surface Preparation

The substrate must be structurally sound. Loose or unsound concrete should be removed and made good. Surfaces must be entirely free of oil, grease, paint, corrosion deposits, dust, laitance or other surface deposits. The surface should be prepared by light grit blasting or high pressure water blasting to produce a lightly exposed aggregate surface.

Mixing

Mix X-Seal EP Primer using the following technique. Add the hardener 'Part B' into the base 'Part A' and mix using a slow speed drill for 2 minutes or until both components have fully dispersed and are uniform in color. Mix only full packs.

Application

Apply a single coat of 100 micron (4 mils) wet film thickness using a brush. If the primer is left to dry for more than 24 hours the surface will have to be re-primed. Porous substrates may require a two coat application. Clean equipment using X-Shield Solvent S.

Limitations

Do not apply below 5C (41C).
Avoid excessive application.
Avoid skin contact.
Do not discard into the water system.

Health and Safety

This product is for industrial use only by trained operatives. It is potentially hazardous if not used correctly. Please refer to the Material Safety Data Sheet (MSDS) prior to the purchase and use of this product. The MSDS can be obtained via our website www.ncc.com.eg

Authorized Technical Specialist

Please note that only NCC X-Calibur Authorized Technical Specialists ('ATSS') are permitted to change any of the information in this data sheet or to provide written recommendations concerning the use of this product. Visit www.ncc.com.eg for a full list of NCC X-Calibur ATSSs.

Datasheet Validity

NCC X-Calibur makes modifications to its product datasheets on a continuous basis. Please check the datasheet update section on www.ncc.com.eg to ensure you have the latest version.

Warranties

NCC X-Calibur supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. NCC X-Calibur does not warrant or guarantee the installation of these products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to NCC X-Calibur in writing within five working days of being detected. NCC X-Calibur Construction Chemistry Inc.

makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied. NCC X-Calibur Construction Chemistry Inc. shall not be liable for damages of any sort including remote or consequential damages, down time, or delay.



Quality Statement
All Products manufactured by NCC X-CALIBUR or imported from X-CALIBUR companies world-wide are manufactured to procedures certified to conform the quality, environment, systems described in the ISO 14001:2004 , ISO 9001:2000.



Hotline: 16960 E-mail: Info@ncc.com.eg Website: www.ncc.com.eg

www.x-calibur.us